

## Import Transportbandgummi Import Rubber conveyor belt



Stärken / thicknesses Einlagen / plies		
Stärke thicknesses (mm)	Formate / dimensions (mm)	Formate / dimensions (mm)
16,0	900 x 70000	1000 x 70000
Weitere Abmessungen auf Anfrage. Other dimensions on request.		

Eigenschaften / properties	Werte / values
Gürtelbreite   belt width (mm)	1200±12
Gürtellänge   belt length (m)	≥100
Dicke obere Abdeckung (mm) top cover thickness	10 (-0.5/+0.5) mm
Dicke unteren Abdeckung (mm) bottom cover thickness	6 (-0.3/+0.3) mm
Zwischenlagen (N/mm) between plies	Min. 5
Zwischen Deckel und Lagen (N/mm) between cover and plies	Min. 4,5
Zerreifestigkeit (N/mm <sup>2</sup> ) tensile strength	Min. 18
Änderung der Zugfestigkeit nach Altern (%) change of tensile strength after aging 70°C, 168 Stunden / 70°C, 168 Hours	±25
Abriebfestigkeit (mm <sup>2</sup> ) abrasion resistant	Max. 150
Dehnung bei 10% Bruchlast (%) elongation at 10% breaking load	Max. 1,5
Änderungsrate der Lautstärke (70 Stunden / 90°C) % rate of volume change (70 Hours / 90°C)	+15
Farbe   colour	schwarz / black
Härte   hardness (Shore A)	65±5

**Hinweis:** Die technischen Kennwerte sind lediglich eine Planungshilfe. Insbesondere stellen sie keine zugesicherten Eigenschaften dar. Die Informationen im Datenblatt beruhen auf Einzelmessungen und unseren derzeitigen Kenntnissen und Erfahrungen. Produktionsbedingte Änderungen vorbehalten.

Wir weisen darauf hin, dass die individuellen Einsatzbedingungen Einfluss auf die Eigenschaften jedes einzelnen Produktes nehmen. Aus diesem Grund ist der Kunde verpflichtet, die Materialien einer Eignungsprüfung zu unterziehen. Der Einsatz unserer Materialien erfolgt ausschließlich im Verantwortungsbereich des Anwenders.

We point out that all information within this catalogue must be considered as rough guidelines. All information provided does not describe any warranted characteristics of materials. The information in this catalogue is based upon individual measurements representing our best knowledge as of the day of measurement. They are subject to technical modifications. We point out that the specific operation conditions may influence the properties of each individual product. For this reason, the customer is required to perform an aptitude test of the materials. The use of our materials is the sole responsibility of the user.

Please note that only the German version of this catalogue is binding in any case. Legal claims can only be based upon the German version. We admit no liability for this English version since it is for explanatory purposes only.